

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Withdrawn and Currently Amended): A manufacturing method of a soft magnetic green compact comprising:

mixing a magnetic powder including an iron system powder and a mixed powder including a resin powder;

compressively molding the magnetic powder and the mixed powder in a mold by a powder metallurgic method in a mold to form a green compact; and

applying thermal treatment to the green compact;

wherein the resin powder includes a lubrication function and a binding function; and

wherein a composition amount of the resin powder ~~assumes~~ is 0.10-3.00 weight percent relative to the total weight before the molding and ~~assumes~~ is 0.01-0.50 weight percent relative to the total weight after the molding and the thermal treatment.

Claim 2 (Withdrawn and Currently Amended): A manufacturing method of a soft magnetic green compact comprising:

mixing a magnetic powder formed by coating an insulation film on a surface of an iron system powder and a mixed powder including a resin powder;

compressively molding the magnetic powder and the mixed powder by a powder metallurgic method with a mold to form a green compact; and

applying thermal treatment to the green compact;

wherein the resin powder includes a lubrication function and a binding function; and  
wherein

a composition amount of the resin powder ~~assumes~~ is 0.10-3.00 weight percent relative to the total weight before the molding and ~~assumes~~ is 0.01-0.50 weight percent relative to the total weight after the molding and the thermal treatment.

Claim 3 (Withdrawn): The manufacturing method of the soft magnetic green compact according to Claim 1, wherein the resin powder includes a polyamide system resin whose maximum particle diameter is equal to or smaller than 200 $\mu$ m.

Claim 4 (Withdrawn): A manufacturing method of a soft magnetic green compact comprising:

mixing a magnetic powder including an iron system powder and a mixed powder including a resin powder;

compressively molding the magnetic powder and the resin powder in a mold by a powder metallurgic method with a mold to form a green compact; and

applying thermal treatment on the green compact;

wherein the resin powder includes a lubrication function and a binding function; and

wherein the resin powder includes a polyamide system resin and a thermoplastic resin having a melting point equal to or higher than 200°C.

Claim 5 (Withdrawn and Currently Amended): The manufacturing method of the soft magnetic green compact according to Claim 4, wherein a composition amount of the polyamide system resin and the thermoplastic resin having the melting point equal to or higher than 200°C ~~assumes~~ is 0.10-3.00 weight percent relative to a total weight before the molding and ~~assumes~~ is 0.01-0.80 weight percent relative to a total weight after the molding and the thermal treatment.

Claim 6 (Withdrawn): The manufacturing method of the soft magnetic green compact according to Claim 4, wherein the thermoplastic resin having the melting point equal to or higher than 200°C includes polyphenylene sulfide system resin.

Claim 7 (Withdrawn): The manufacturing method of the soft magnetic green compact according to Claim 1, wherein the thermal treatment is performed at 100-450°C.

Claim 8 (Withdrawn): The manufacturing method of the soft magnetic green compact according to Claim 1, wherein the green compact after the thermal treatment includes density of 6.6-7.4 g/cm<sup>3</sup>.

Claim 9 (Withdrawn): The manufacturing method of the soft magnetic green compact according to Claim 1, wherein the thermal treatment is performed at oxidizing ambient.

Claim 10 (Currently Amended): A soft magnetic green compact comprising:  
a magnetic powder including an iron system powder;  
a mixed powder including a resin powder;  
a green compact formed by compressively molding the magnetic powder and the mixed powder by a powder metallurgic method, the green compact applied with thermal treatment; and  
the resin powder including a lubrication function and a binding function;  
wherein a composition amount of the resin powder ~~assumes~~ is 0.10-3.00 weight percent relative to the total weight before the molding and ~~assumes~~ is 0.01-0.50 weight percent after the molding and the thermal treatment.

Claim 11 (Currently Amended): A soft magnetic green compact comprising:  
a magnetic powder including an iron system powder with an insulation coating  
~~provided with an insulation film coating on a surface thereof;~~  
a mixed powder including a resin powder;  
a green compact formed by compressingly molding the magnetic powder and the resin powder in a mold by a powder metallurgic method, the green compact applied with thermal treatment; and  
the resin powder including a lubrication function and a binding function;  
wherein a composition amount of the resin powder ~~assumes~~ is 0.10-3.00 weight percent relative to the total weight before the molding ~~and assumes~~ is 0.01-0.50 weight percent relative to the total weight after the molding and the thermal treatment.

Claim 12 (Original): The soft magnetic green compact according to Claim 10, wherein the resin powder includes a polyamide system resin whose maximum particle diameter is equal to or smaller than 200 $\mu$ m.

Claim 13 (Currently Amended): ~~[[A]]~~ The soft magnetic green compact ~~comprising:~~  
according to Claim 10,

~~a magnetic powder including an iron system powder;~~  
~~a mixed powder including a resin powder;~~  
~~a green compact formed by compressively molding the magnetic powder and the mixed powder by a powder metallurgic method, the green compact applied with thermal treatment; and~~  
~~the resin powder including a lubrication function and a binding function;~~

wherein the resin powder includes a polyamide system resin and a thermoplastic resin having a melting point equal to or higher than 200°C.

Claim 14 (Original): The soft magnetic green compact according to Claim 13, wherein the thermoplastic resin having the melting point equal to or higher than 200°C includes a polyphenylene sulfide system resin.

Claim 15 (Original): The soft magnetic green compact according to Claim 10, wherein the thermal treatment is performed at 100-450°C.

Claim 16 (Original): The manufacturing method of the soft magnetic green compact according to Claim 10, wherein the green compact after the thermal treatment includes density of 6.6-7.4 g/cm<sup>3</sup>.

Claim 17 (Canceled).

Claim 18 (New): A soft magnetic green compact comprising:  
a magnetic powder including an iron system powder;  
a resin powder;  
a green compact formed by compressively molding the magnetic powder and the resin powder by a powder metallurgic method, the green compact applied with thermal treatment;  
and  
the resin powder including a lubrication function and a binding function;  
wherein a composition amount of the resin powder is 0.01-0.50 weight percent relative to the total weight after the molding and the thermal treatment; and

powder particles of the magnetic powder are bound to each other by oxidization.

Claim 19 (New): A soft magnetic green compact comprising:

a magnetic powder including an iron system powder provided with an insulation film coating on a surface thereof;

a resin powder;

a green compact formed by compressively molding the magnetic powder and the resin powder by a powder metallurgic method, the green compact applied with thermal treatment; and

the resin powder including a lubrication function and a binding function;

wherein a composition amount of the resin powder is 0.01-0.50 weight percent relative to the total weight after the molding and the thermal treatment; and

powder particles of the magnetic powder are bound to each other by oxidization.

Claim 20 (New): The soft magnetic green compact according to Claim 10, wherein the thermal treatment is performed at 250-450°C and at oxidizing ambient.

Claim 21 (New): The soft magnetic green compact according to Claim 11, wherein the thermal treatment is performed at 250-450°C and at oxidizing ambient.

Claim 22 (New): The soft magnetic green compact according to Claim 11, wherein the insulation film includes phosphoric acid system film formed by phosphoric conversion treatment.

Claim 23 (New): The soft magnetic green compact according to Claim 22,

Application No. 10/688,890  
Reply to Office Action of October 26, 2005

wherein the insulation film of the magnetic powder is bound by oxidization.

SUPPORT FOR THE AMENDMENT

Claims 1, 2, 5, 10, and 11 are currently amended.

Claim 17 is canceled.

Claims 18-23 are added.

The claims have been amended for editorial purposes and to clarify the claim language. The amendments to the claims are supported by the claims and the specification, as originally filed.

New claims 18-23 are supported by the claims, as originally filed, and the specification, as originally filed, e.g., at paragraphs [0032], [0041], [0056], and [0073].

No new matter is believed to be added by the amendments.

Upon entry of these amendments, Claims 1-16 and 18-23 will be pending in this application. Claims 1-9 are currently withdrawn from consideration by the Examiner, in view of a Restriction Requirement.